

Isofrax® 1260C is a revolutionary new fibre with a unique, patented silica-magnesia chemistry. Designed to be used in a wide variety of demanding, high temperature applications, Isofrax has very high solubility in simulated body fluids and meets the European and German regulatory requirements.

Isofrax 1260C Mastics are newly developed insulating products for use in high temperature industrial applications where patching and filling of voids is required. Isofrax 1260C Mastics show good strength and resistance to shrinkage in operational environments and are easy to install.



GENERAL CHARACTERISTICS

Isofrax Pumpable Mastic

Isofrax Pumpable Mastic is a pumpable product designed for use with a variety of hand operated and pneumatic applicators.

Typical applications include:

- Hot or cold repairs of boilers
- Caulking of expansion joints and cracks in anode baking pits
- Insulation of furnace penetrations (e.g. tubes, tube hangers & thermocouples)

Isofrax Moldable Mastic

Isofrax Moldable Mastic is a moldable putty-like product which requires drying to produce a hard surfaced, low shrinkage insulator.

Typical applications include:

- Incinerator packing/insulation
- General packing applications
- Piece moulding

TYPICAL PRODUCT PARAMETERS

Typical Physical Properties

Grade	Pumpable	Moldable
Colour	White	White
Product Form	Tacky putty	Tacky putty
Maximum Rec	1260°C	1260°C
Operating Temp		
Wet Density	1090 kg/m ³	1140 kg/m ³
Dry Density *	270 kg/m ³	340 kg/m ³

Thermal Conductivity Data (W/mK)*

Mean Temp.	Pumpable	Moldable
600°C	0.09	0.21
800°C	0.13	0.25
1000°C	0.19	0.31

* Dry Density & Thermal Conductivity values are for guidance only. Actual values are dependent upon installed characteristics.

Shelf life

Isofrax 1260C Mastics can be stored for up to 6 months if kept unopened in cool, dry conditions. Excessive heat will shorten shelf life and freezing will damage the product. Storage between 5°C and 20°C is recommended.

Important note !

Isofrax Pumpable Mastic can be easily installed using the approved equipment. Details of recommended pump units, applicator tools and caulking guns are available from your Unifrax local sales office. For first time users it is recommended that Unifrax be contacted for detailed installation advice.

After installation and during first firing of **Isofrax 1260C Mastics** some initial outgassing can be expected at elevated temperatures. In some situations forced drying at 90-150°C may be beneficial.

Availability

Isofrax Pumpable Mastic is available in the following packaging:

1500ml sachets
5kg & 20kg pails



The 1500ml sachets are for use with either air or hand operated applicator tools. The material in the 20kg pail is supplied pre-packed for use with the recommended pump unit. This is essential for a successful pumping operation.

Isofrax Moldable Mastic is available in the following packaging:

5kg & 20kg pails

Supplied by:

Contact numbers

Website: www.unifrax.com

United Kingdom

Tel: +44 (0) 1744 88 7600 Fax: +44 (0) 1744 88 9916

France

Tel: +33 (0) 4 77 73 98 25 Fax: +33 (0) 4 77 73 39 91

Germany

Tel: +49 (0) 211 87 746 0 Fax: +49 (0) 211 87 746 115

Belgium

Tel: +32 (0)2 761 23 12 Fax: +32 (0)2 761 23 13

Italy

Tel: +39 02 96701808 Fax: +39 02 9625721

Spain

Tel: +34 91 395 22 79 Fax: +34 91 395 21 24

Handling Information

A Material Safety Data Sheet has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.



Information contained in this publication is for illustrative purposes only and is not intended to create any contractual obligation.

Further information and advice on specific details of the products described should be obtained in writing from a Unifrax Corporation company (Unifrax Benelux, Unifrax España, Unifrax France, Unifrax GmbH, Unifrax Italia, Unifrax Limited).

Unifrax maintains a continuous programme of product development and reserves the right to change product specifications without prior notice. Therefore, it remains at all times the responsibility of the customer to ensure that Unifrax materials are suitable for the particular purpose intended.

Similarly, insofar as materials not manufactured nor supplied by Unifrax are used in conjunction with or instead of Unifrax materials, the customer should ensure that all technical data and other information relating to such materials has been obtained from the manufacturer or supplier. Unifrax accepts no liability arising from the use of such materials.

All sales made by a Unifrax Corporation company are subject to that company's Terms and Conditions of Sale, copies of which are available on request.